

Chemical Resistance Data

Stronghold (GM006X) & Stronghold+ (GM007X)

Chemical	EN374 performance level
Benzalkonium chloride	6
Formaldehyde (37%)	6
Glutaraldehyde (50%)	6
Isopropanol	2
Isopropyl acetate	0
Methanol	0
n-Hexane	0
Paraformaldehyde (50%)	6
Peracetic acid 5%	5
Phenol (1%)	0
Phenol (10%)	0
Sodium hydroxide 40%	6
Versenol 120 (Trisodium N-(hydroxyethyl)-ethylenediaminetriacetate)	6

EN374 performance levels

Performance level	1	2	3	4	5	6
Breakthrough time (mins)	>10	>30	>60	>120	>240	>480

This data is intended to guide and inform only and is not subject to any guarantee on the part of Unigloves UK Ltd. Conditions of use are ultimately beyond our control and because it is impossible to test all chemicals and combinations of chemicals, users are advised to determine the suitability of any glove before use.