



Permeation times for glove 8190 according to EN 374-3

Code	Chemical	Formula	Minutes	Level	Lab
	Nitric acid 70%	HNO ₃	> 480 min	6	a)
J	n-Heptan	C ₇ H ₁₆	13 min	1	b)
K	Sodium hydroxide 40%	NaOH	> 480 min	6	b)
L	Sulfuric acid 96%	H ₂ SO ₄	180 min	4	b)

a) Issud by:

Notified Body 1065
LRCCP, Laboratoire de Recherches et de Contrôle du Caoutchouc et des Plastiques
60 Rue Auber
94408 Vitry Sur Seine Cedex
France

Certificate 0076/065/162/04/99/0002

b) Issued by:

Notified Body 0197
TÜV Rheinland LGA Products GmbH
Tillystrasse 2
D-90431 Nürnberg
Germany

Certificate BP 60041641 0001