

Alto 258

Chemical Product	CAS #	Breakthrough time (minutes)	Permeation level	Standard	Degradation level	Rating
1,1,1-Trichloroethane 99%	71-55-6	10	0	EN 374-3:2003	1	-
2-Nitropropane 99%	79-46-9	18	1	EN 374-3:2003	3	=
2-Propanol (Isopropanol) 99%	67-63-0	40	2	EN 374-3:2003	4	+
Acetic acid 99%	64-19-7	21	1	EN 374-3:2003	3	=
Acetone 99%	67-64-1	5	0	EN 374-3:2003	3	=
Butyl Acetate 99%	123-86-4	10	0	EN 374-3:2003	2	-
Cyclohexane 99%	110-82-7	7	0	EN 374-3:2003	1	-
Dimethylformamide 99%	68-12-2	30	1	EN 374-3:2003	4	+
Dimethylsulfoxide 99%	67-68-5	190	4	EN 374-3:2003	4	++
Ethanol 95%	64-17-5	17	1	EN 374-3:2003	3	=
Ethyl acetate 99%	141-78-6	3	0	EN 374-3:2003	2	-
Ethylene glycol 99%	107-21-1	NT	NT		4	NA
Formaldehyde 37%	50-00-0	480	6	EN 16523-1:2015	NT	NA
Hydrochloric acid 10%	7647-01-0	480	6	EN 374-3:2003	NT	NA
Hydrochloric acid 35%	7647-01-0	480	6	EN 374-3:2003	NT	NA
Hydrofluoric Acid 40%	7664-39-3	480	6	EN 16523-1:2015	NT	NA
Hydrogen peroxide 30%	7722-84-1	480	6	EN 16523-1:2015	3	++
Methanol 99%	67-56-1	26	1	EN 374-3:2003	3	=
Methyl Ethyl Ketone (2-Butanone) 99%	78-93-3	6	0	EN 374-3:2003	3	=
Methyl methacrylate 95%	80-62-6	5	0	EN 374-3:2003	3	=
Methylisobutylketone 99%	108-10-1	6	0	EN 374-3:2003	3	=
N-methyl-2-Pyrrolidone 99%	872-50-4	60	2	EN 374-3:2003	4	+
Naphtha, Hydrotreated Heavy mixture	64742-48-9	7	0	EN 374-3:2003	1	-
Phosphoric acid 75%	7664-38-2	480	6	EN 374-3:2003	4	++
Sodium hydroxide 20%	1310-73-2	480	6	EN 374-3:2003	NT	NA
Sodium hydroxide 40%	1310-73-2	480	6	EN 16523-1:2015	3	++
Sodium hydroxide 50%	1310-73-2	480	6	EN 374-3:2003	NT	NA

*not normalized result

Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to breakthrough time based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative breakthrough time based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed unsuitable for work with this chemical.

 NT : Not tested

 NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time

Alto 258

Chemical Product	CAS #	Breakthrough time (minutes)	Permeation level	Standard	Degradation level	Rating
Styrene 99%	100-42-5	2	0	EN 374-3:2003	1	-
Sulfuric acid 96%	7664-93-9	83	3	EN 374-3:2003	NT	-
t-Butyl Methyl Ether 98%	1634-04-4	8	0	EN 374-3:2003	2	-
Tetrahydrofurane 99%	109-99-9	2	0	EN 374-3:2003	1	-
Toluene 99%	108-88-3	6	0	EN 374-3:2003	1	-
Trichloroethylene 99%	79-01-6	1	0	EN 374-3:2003	1	-
Vinyl acetate 99%	108-05-4	3	0	EN 374-3:2003	3	=
Xylene 99%	1330-20-7	4	0	EN 374-3:2003	1	-

*not normalized result

Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to breakthrough time based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative breakthrough time based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed unsuitable for work with this chemical.
- NT : Not tested
- NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time